



**ALTA 2023 Gold-PM Keynote Presentation**

# **Chloride – A Precious Metals Leaching System yet to Reach its Potential**

**By  
Mike Adams, Keith Liddell**

**Presenter: Dr Mike Adams  
[mike.adams@lifezonemetals.com](mailto:mike.adams@lifezonemetals.com)**

# Disclaimer

---

**By accepting this presentation, recipients acknowledge that they have read, understood and accepted the terms of this notice and disclaimer.**

This presentation is the property of, and may contain the proprietary and confidential information of, Lifezone Metals Limited and its group of companies (collectively, the “Company”).

The reproduction or transmission of all or any part of the work, whether by copying, photocopying or storing in any medium by electronic means or otherwise, without the written permission of the Company, is strictly prohibited. All rights are expressly reserved to the Company.

This presentation is provided for informational purposes only and is intended solely to facilitate a discussion with the recipient(s). No representation or warranty, express or implied, is or will be given by the Company or its affiliates, directors, officers, employees, or any other person as to the accuracy, completeness, reasonableness or fairness of any information contained in this presentation.

No responsibility or liability whatsoever is accepted for the contents, accuracy, omissions, or for any errors or statements in this presentation. No information in this presentation constitutes, nor can it be relied upon, as advice.

# Background


---

Chloride leaching of precious metals





# Discovery of Aqua Regia and Chlorine



Aqua Regia was discovered by Persian alchemist Jabir Ibn Hayyan (720-813) by the mixture of hydrochloric and nitric acids








Chlorine was discovered by the Swedish chemist Carl Wilhelm Scheele (1742-1786) by the action of hydrochloric acid on manganese dioxide in 1774

# Early Chlorination Processes for Gold Extraction

Process	Date	Pretreatment	Equipment	Treatment	Leach	Recovery
Plattner	1848	Dead roast	Damp fixed bed vat	Cl <sub>2</sub> permeation	Water percolation	FeSO <sub>4</sub> reduction
Duflos	1848	-	Damp fixed bed vat	In leach	Supersaturated Cl <sub>2</sub> percolation	Reduction
Mears	1877	-	Rotating barrel	Cl <sub>2</sub> 300 kPa	Water leach	Reduction
Thies	1881	-	Rotating barrel	In leach	CaOCl <sub>2</sub> /H <sub>2</sub> SO <sub>4</sub> leach 30 kPa	Reduction
Lange	1885	-	Earthenware pots	Cl <sub>2</sub>	Water leach	H <sub>2</sub> S reduction
Munktell	1888	Dead roast	Damp fixed bed vat	Hot water then HCl or H <sub>2</sub> SO <sub>4</sub> for Cu/Fe removal	CaOCl <sub>2</sub> /H <sub>2</sub> SO <sub>4</sub> leach	Lead acetate

Early Processes for Generation of Chlorine:






# Factors in the Replacement of Gold Chlorination by Cyanidation

- Excess chlorine losses due to volatilisation from leaky vessels
- Excess chlorine consumption due to reaction with sulphides
- Excess chlorine consumption due to reaction with base metals

2. Cyanide Extraction. — Within the last few years it has been found that a weak solution (*e.g.*, 1 per cent. or under) of potassium cyanide can be profitably used for extracting gold, especially from the poor tailings of other processes. The reaction said to occur is—



Robinson GM, 1890



Simmer & Jack, 1893

# Chemistry of Chlorination

---

Precious metals leaching reactions




# Chloride Leaching Chemistry

---

## Gold chlorination chemistry




## PGM chlorination chemistry






# Potential-pH Diagram for Pt-Cl-H<sub>2</sub>O and Pd-Cl-H<sub>2</sub>O Systems




ELEMENTS	Molality	Pressure
Pt	4.100E-05	1.000E+00
Cl	6.200E+00	1.000E+00




ELEMENTS	Molality	Pressure
Pd	4.100E-05	1.000E+00
Cl	6.200E+00	1.000E+00

# Potential-pH Diagram for Rh-Cl-H<sub>2</sub>O System




ELEMENTS	Molality	Pressure
Rh	4.100E-05	1.000E+00
Cl	6.200E+00	1.000E+00

# Potential-pH Diagram for Au-Cl-H<sub>2</sub>O and Ag-Cl-H<sub>2</sub>O Systems



$a_{\text{Au}} = 10^{-3}$  and  $a_{\text{Cl}} = 1$  (solid) and  $= 5$  (dashed); 25°C  
Kelsall et al., 1993



$a_{\text{Au}} = 10^{-4}$  and  $a_{\text{Cl}} = 1$  (solid) and  $= 2$  (dashed); 25°C  
Welham et al., 1993

# Chloride-Based Leaching Processes

---

Gold and PGM recovery



# Chloride-Based Leaching Processes for Gold

Process	Ligand	Oxidant	Tested	Application Level	References
Hydrocopper	Cl <sup>-</sup>	Cu <sup>2+</sup> , O <sub>2</sub>	D		Hyvärinen and Hämäläinen (2005), Canadian Mining Journal (2006), and Infomine (2008); Lundström et al (2009, 2011, 2012)
Intec	Cl <sup>-</sup> /Br <sup>-</sup>	Cu <sup>2+</sup> , Fe <sup>3+</sup>	P		Moyles (1999), Severs (1999), and Monument Mining Ltd (2016)
Lifezone Metals	Cl <sup>-</sup>	Cl <sub>2</sub>	P	FS (2x sites, South Africa)	<b>Liddell (2009), Liddell et al. (2011), Liddell and Adams (2012a,b), Adams et al. (2015, 2019, 2020)</b>
N-Chlo	Cl <sup>-</sup> /Br <sup>-</sup>	Cu <sup>2+</sup> , Fe <sup>3+</sup>	D		Nippon Mining and Metals (2008)
Neomet	Cl <sup>-</sup>	Cu <sup>2+</sup> , Fe <sup>3+</sup> HNO <sub>3</sub> O <sub>2</sub> H <sub>2</sub> O <sub>2</sub>	P		Harris and White (2011a,b, 2013)
Nichromet	Cl <sup>-</sup> /Br <sup>-</sup>	Cl <sub>2</sub> /Br <sub>2</sub>	P		Lalancette (2009), and Lemieux et al. (2014)
Outotec	Cl <sup>-</sup> /Br <sup>-</sup>	Cu <sup>2+</sup> , Fe <sup>3+</sup>	P		Miettinen et al. (2013)
Platsol	Cl <sup>-</sup>	O <sub>2</sub>	P	FS (Northmet, USA)	Ferron et al. (2000, 2003), Wardell-Johnson et al. (2009), Dreisinger et al (2016)



# Chlorination in Platinum Refineries

A heated agitated 2.2 m<sup>3</sup> titanium vessel for batch dissolution of a PGM concentrate via intermittent chlorine sparging



Photograph courtesy of Impala Platinum  
(after Crundwell et al 2012)

# Platinum-Group Metals Refineries

Parameter	Unit	Lonmin	Kratsvetmet	Vale Acton	JM/Anglo	Impala
<b>Main feed material</b>		Leached matte	Anode slime	Concentrate/ Catalyst/ E-Waste	Leached mag concentrate	Leached matte
<b>HCl</b>	g/L	219	175			109
<b>Temperature</b>	C	65	70	90-98	120	65-70
<b>Pressure</b>	bar	1	3	1	4	0.7
<b>Residence time</b>	h	6	2			8
<b>Material</b>		Glass-lined	Ti			Ti Gr2; jacketed
<b>Volume</b>	m3	2.2	1			2.5
<b>Impeller</b>		Pitched-blade turbine	Hollow shaft inductor			Pitched-blade turbine
<b>Free Cl<sub>2</sub> removal</b>		Air sparging				"Dechlorinated"
<b>Gold recovery method</b>		N <sub>2</sub> H <sub>4</sub> reduction/HCl	Precipitate with concentrate	SX	SX	IX
<b>Gold product</b>		Crude gold	99.99% Au	99.99	99.95	99.95
<b>Typical gold recovery</b>	%	99	98	99	99.5	94
<b>First-pass yield</b>	%	92		98	84	98

# Lifezone Metals

---


Gold and PGM Hydromet Processing



# Lifezone Metals Hydromet – Overcoming the Chlorination Limitations

## The globally patented hydrometallurgical Lifezone Metals Process:

- **Chlorine losses** due to volatilisation
  - minimised via properly engineered vessels
- **Chlorine consumption** due to reaction with sulphides and base metals
  - eliminated via prior removal of these reagent consumers by pressure oxidation
- **Gas-liquid-solid contact** constraints in static and rolling reactors
  - eliminated by use of modern CSTR reactors
- **Refractory, complex** and deleterious PGM-Au-gangue mineral phases
  - eliminated by heat treatment conditioning and preleach prior to chlorination



# Lifezone Metals Hydromet Process Background

---

## **The globally patented hydrometallurgical Lifezone Metals Process:**

- Developed for the extraction of platinum group metals (PGM), gold, silver and base metals from PGM sulphide flotation concentrates without smelting or cyanidation
- Successfully demonstrated on various PGM and polymetallic concentrates, including UG2, Merensky, Platreef and Great Dyke from southern Africa and polymetallic concentrates from North America, Australia and Africa.
- High recoveries (94 % - 99 %) for selective extraction of a range of value metals, including precious metals (Pt, Pd, Rh, Au, Ag) and base metals (Ni, Co, Cu, Zn, Sn, Pb, Mo) with stabilization of impurities such as As and S without gaseous emissions.
- KellGold process variation for refractory gold, Cu/Au and preg-robbing gold concentrates, enabling production of refined metals at the mine site without the use of cyanide
- Licensed as Kell Process in SADC region via KellTech Ltd, along with shareholders Sedibelo Platinum and IDC (Industrial Development Corporation of South Africa)



# Lifezone Metals Hydromet – Technical Features

---


Patented process comprising four basic sequential steps, all of which are well proven and commonly used in the metallurgical industry and provide high recoveries of base and precious metals:

1. **Aqueous pressure oxidation** in an acidic sulphate medium to dissolve the sulphides and remove the base metals while minimising dissolution of the precious metals, producing copper, nickel and cobalt products;
2. **Heat treatment** of the pressure oxidation residue as required, to condition the mineral phases, rendering the material amenable for subsequent leaching;
3. **Atmospheric leaching** of the iron and other gangue components in chloride media;
4. **Atmospheric leaching of the PGM and gold** in chloride medium in a similar manner as typically used in PGM refineries, with PGM and gold recovery to high-purity products

Separate leaching stages for the precious metals and base metals:

- keeps sulphate and chloride chemistries separate
- small autoclave and tanks – fast leach kinetics
- optimizes selection of materials of construction
- fast production of metals and low lock-up of value

# Lifezone Metals Hydromet – Comparison with Smelting




# Lifezone Hydromet Testwork – Metals Extraction Results

PGM-Au-Ni-Cu-Co Concentrate		Overall Recoveries into Solution (%)						
Sample ID	Type	Pt	Pd	Rh	Au	Ni	Cu	Co
Kabanga Nickel Scoping Test Results - Test 1 <sup>(1)</sup>		-	-	-	-	98.5	96.9	97.5
Kabanga Nickel Scoping Test Results - Test 2 <sup>(1)</sup>		-	-	-	-	99.7	99.6	99.8
A	UG2	99	97	93	99	97	93	99
B	UG2	99	98	96	97	95	96	83
C	Merensky	99	98	97	99	99	99	98
D	UG2-Merensky	99	98	96	99	98	99	93
E	Platreef	99	98	96	99	99	99	99
F	Platreef	98	99	97	96	99	99	99
G	Polymetallic Great Lakes	97	99	95	96	99	99	99
H	Polymetallic Great Lakes	99	99	-	99	99	99	99
I	UG2-Merensky	99	98	90	99	97	96	95
J	Polymetallic North America	95	99	-	99	99	99	98
K	Great Dyke	99	98	95	98	98	98	96
L	Great Dyke	99	98	89	99	99	99	96
M	Polymetallic Australia	99	99	-	92	99	99	93
N	Platreef	98	99	-	97	99	99	99
O	Platreef	97	93	93	94	99	99	98
P	Platreef	99	98	94	97	99	99	98
Q	Ni-Cu-Co Sulphide	-	-	-	-	98	99	99
	Mean	98	98	94	97	98	98	96
Au-Ag-Cu-Co-Zn-Pb-Sb Concentrate		Overall Recoveries into Solution (%)						
Sample ID	Type	Au	Ag	Zn	Pb	Cu	Co	Sb
1	High-grade carbonaceous polymetallic ore	91	95	99	95	98	-	-
2	Refractory gold concentrate	96	-	-	-	98	97	-
3	Refractory gold polymetallic concentrate	98	97	99	97	99	-	95
4	Double refractory Cu-Au concentrate	98	98	-	-	99	-	-
5	Refractory gold concentrate	98	98	-	-	-	-	-
	Mean	96	97	100	96	99	97	95

Source: Company Study by Liddell, K.S., Adams, M.D., Smith, L.A., and Muller, B Kell hydrometallurgical extraction of precious and base metals from flotation concentrates –Piloting, engineering, and implementation advances. Published in the Journal of the Southern African Institute of Mining and Metallurgy (2019). Testing was performed at Simulus Laboratories in Perth, Australia.


1 – Kabanga nickel results are based upon a scoping sample used in a pressure oxidation test performed at Simulus Laboratories in Perth, Australia on August 8, 2022.

## Comparison of Environmental Profiles



(after Smith, Adams, and Liddell, 2019)

## Comparison of Working Capital Value Lockup (In-process Metal Inventory)





# Outlook

---


## Chloride-Based Leaching Systems



# Outlook for Chloride-Based Leaching Systems

---

- Several chloride-based leaching systems have been tested in recent years at batch or pilot scale
- Lifezone Metals technology is at DFS or Detail Design stage for several commercial-scale applications
- Implementation of bulk chloride-based leaching systems at commercial scale is likely to take place in the next few years



# Acknowledgements

---

**Lifezone Metals**

**Simulus Engineers & Laboratories**



The supply chain solution for clean metals

